

Return address: P.O. box 337, 7500 AH Enschede, The Netherlands

Superior Manufacturing Group – Europe B.V.  
Att. Mrs. G. Dirckx  
Achterzeedijk 57  
2992 SB  
Barendrecht  
The Netherlands

TÜV Rheinland Nederland B.V.  
The Netherlands

Postal address:  
P.O. Box 337  
7500 AH Enschede

Parking and delivery:  
Josink Esweg 10  
7545 PN Enschede

[www.tuv.com/nl](http://www.tuv.com/nl)

T +31 88 888 7888  
F +31 88 888 7859

[Jaring.de.Wolff@nl.tuv.com](mailto:Jaring.de.Wolff@nl.tuv.com)

## REPORT

**Project number** : 89206690  
**Report number** : 89206690.05en

**Date**  
08-10-2014

**Project number**  
89206690

**Report number**  
89206690.05en

### **Received:**

A industrial mat, a floor covering, marked as: "620 Diamond Flex Lok", size 910 mm x 910 mm; TÜV-reference MT14-48336.05.

The samples have been received on 23-09-2014. The samples are selected by the applicant. The test house has had no influence on the sampling procedure.

**Phone number client**  
+31 180 643 115

### **Order:**

To determine the slip resistance according to DIN 51130, ramp test.  
The space of displacement is not determined.

**Fax number client**  
+31 180 611 551

### **Results:**

See page two.

**Article**  
620 Diamond Flex Lok

### **Appendix:**

None

**Appendix**  
-none-

## RESULTS

### *Slip resistance*

Method DIN 51130:2013-5

Testing location : Subcontracted to an accredited laboratory.  
Date of testing : 30-09-2014

Mean angle of acceptance,  $\alpha_{ges}$  : 13.2°  
Slip resistance classification : R10\*

\* R10 requirement =  $10^\circ < \alpha_{ges} \leq 19^\circ$

Date  
08-10-2014

Project number  
89206690

Report number  
89206690.05en

Article  
620 Diamond Flex Lok

Page  
2/2

Author:  
Mr. J. de Wolff



Visa:  
Mr. R. Boerboom



*All rights reserved.*

*No part of this report may be reproduced, provided to and/or examined by third parties, and/or published by print, photoprint, microfilm, in electronic form or any other means without the explicit previous written consent of TÜV Rheinland Nederland B.V. The results are based upon the samples received and have not to be representative for the total production. Besides TÜV Rheinland Nederland B.V. had no influence on the sampling. In case this report was drafted within the context of an assignment to TÜV Rheinland Nederland B.V., the rights and obligations of contracting parties are subject to the General Terms & Conditions for Advisory, Research and Certification assignments to TÜV Rheinland Nederland B.V. and/or the relevant agreement concluded between the contracting parties.*

© 2010 TÜV Rheinland Nederland B.V.