

Prestige Carpets bvba
Dhr. Christoph Bittner
Klein Frankrijkstraat 14
9600 RONSE



Your notice of
11-08-2017

Your reference

Date
08-09-2017

Analysis Report 17.04668.01

Required tests :

EN 13501-1 (2007) + A1 (2009)

Identification number	Information given by the client	Date of receipt
T1717655	Fork Lift mats	11-08-2017

Kristina De Temmerman

Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

Inrichting erkend bij toepassing van de besluitwet van 30-01-1947 • Établissement reconnu par application de l'arrêté-loi du 30-01-1947
GENT • Technologiepark 7 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be
GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be
KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 281828 • fax +32 56 281830 • info@vkc.be
VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB

Reference: T1717655 - Fork Lift mats

Information given by the client

Product standard	EN 13501-1 (2007) + A1 (2009)
FR treated	no
FR-surface treatment	no
Type of manufacture	Flat needle felt
Use-surface	Polypropylene
Backing layer	SBR rubber
Total mass	5 kg/m ²
Total thickness	2.5 cm
Surface structure	Flat

Notified body No: 0493

Reference: T1717655 - Fork Lift mats

Reaction to fire tests – Ignitability of building products subjected to direct impingement of flame - Single-flame source test

Date of ending the test 06-09-2017
 Standard used EN ISO 11925-2 (2010)
 Product standard EN 13501-1 (2007) + A1 (2009)

Floor covering

Deviation from the standard -

Conditioning 23°C, relative humidity 50%
 Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Substrate Fibre cement board - density (1800 ± 200) kg/m³
 Mounting Loose-laid
 Cleaning Specimens have not been cleaned

Flame application time (s) 15
 Flame application Surface

	Length			Width		
	1	2	3	4	5	6
Time to reach 150 mm mark (s)	*	*	*	*	*	*

* = time to reach the mark > 20 s or mark not reached

Criteria Floorcoverings

time to reach the mark: - > 20 s : Class Efl
 - ≤ 20 s : Class Ffl

Classification Class E_{fl}

Limitations

This classification document does not represent type approval or certification of the product.

Reference: T1717655 - Fork Lift mats

Reaction to fire tests for floorings - Determination of the burning behaviour using a radiant heat source

Date of ending the test	06-09-2017
Standard used	EN ISO 9239-1 (2010)
Product standard	EN 13501-1 (2007) + A1 (2009)
Deviation from the standard	-
Conditioning	23°C, relative humidity 50% Minimum 14 days or until constant mass is achieved

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Test specimen

Substrate	Fibre cement board - density (1800 ± 200) kg/m ³
Mounting	Loose-laid
Cleaning	Specimens have not been cleaned

Radiant heat flux

	Flame spread distance (cm)			Flame time	Heat flux * kW/m ²
	10 min	20 min	30 min		
Width					
#1	30	35	35	22 min 45 s	6.4
Length					
#1	25	37	37	20 min 55 s	6.0
#2	25	37	38	22 min 55 s	5.8
#3	30	38	38	22 min 35 s	5.8
Average					5.9

* Heat flux at the time of flame extinguishment or after a test duration of 30 minutes.

Fire classification in accordance with EN 13501-1 (2007) + A1 (2009)		
Class	EN ISO 11925-2 or CWFT	EN ISO 9239-1 (test duration = 30 min)
B _{fl}	E _{fl}	heat flux ≥ 8,0 kW/m ²
C _{fl}	E _{fl}	heat flux ≥ 4,5 kW/m ²
D _{fl}	E _{fl}	heat flux ≥ 3,0 kW/m ²

Smoke production: Light attenuation

	Maximum (%)	Total (%.min)
Width		
#1	59	487
Length		
#1	60	475
#2	59	482
#3	69	440
Average		466

Additional classification in accordance with EN 13501-1 (2007) + A1 (2009)	
smoke production ≤ 750%.min	s1
smoke production > 750%.min	s2

Reaction to fire classification : C_n/ s1

*Loose-laid on a non-combustible substrate**

** End use substrates of classes A1 or A2-s1, d0 (ISO 13238:2010 § 5.2.2)*

Limitations

This classification document does not represent type approval or certification of the product.

“The classification assigned to the product in this report is appropriate to a declaration of performance by the manufacturer within the context of system 3 of assessment and verification of constancy of performance and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the products design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.”